



BREAKING THE 20% EFFICIENCY BARRIER

Q.ANTUM DUO Z Technology with zero gap cell layout boosts module efficiency up to 21.4%.



THE MOST THOROUGH TESTING PROGRAMME IN THE INDUSTRY

Q CELLS is the first solar module manufacturer to pass the most comprehensive quality programme in the industry: The new "Quality Controlled PV" of the independent certification institute TÜV Rheinland.



INNOVATIVE ALL-WEATHER TECHNOLOGY

Optimal yields, whatever the weather with excellent low-light and temperature behavior.



ENDURING HIGH PERFORMANCE

Long-term yield security with Anti LID Technology, Anti PID Technology¹, Hot-Spot Protect and Traceable Quality Tra.Q™.



EXTREME WEATHER RATING

High-tech aluminum alloy frame, certified for high snow (5400 Pa) and wind loads (4000 Pa).



A RELIABLE INVESTMENT

Inclusive 12-year product warranty and 25-year linear performance warranty².

- $^{\rm 1}$ APT test conditions according to IEC /TS 62804-1:2015, method A (–1500 V, 96 h)
- ² See data sheet on rear for further information.


THE IDEAL SOLUTION FOR:





MECHANICAL SPECIFICATION

Format	74.0 in \times 41.1 in \times 1.26 in (including frame) (1879 mm \times 1045 mm \times 32 mm)
Weight	48.5 lbs (22.0 kg)
Front Cover	0.13in (3.2mm) thermally pre-stressed glass with anti-reflection technology
Back Cover	Composite film
Frame	Black anodized aluminum
Cell	6 × 22 monocrystalline Q.ANTUM solar half cells
Junction Box	2.09-3.98 in × 1.26-2.36 in × 0.59-0.71 in (53-101 mm × 32-60 mm × 15-18 mm), IP67, with bypass diodes
Cable	4 mm² Solar cable; (+) ≥49.2 in (1250 mm), (-) ≥49.2 in (1250 mm)
Connector	Stäubli MC4, Hanwha Q CELLS HQC4; IP68




ELECTRICAL CHARACTERISTICS

VER CLASS			395	400	405	410	415
IMUM PERFORMANCE AT STANDARD TEST	CONDITIO	NS, STC ¹ (PO	WER TOLERANCE +	5W/-0W)			
Power at MPP ¹	P _{MPP}	[W]	395	400	405	410	415
Short Circuit Current ¹	I _{sc}	[A]	11.13	11.16	11.19	11.22	11.26
Open Circuit Voltage ¹	V _{oc}	[V]	45.03	45.06	45.09	45.13	45.16
Current at MPP	I _{MPP}	[A]	10.58	10.64	10.70	10.76	10.82
Voltage at MPP	V _{MPP}	[V]	37.32	37.59	37.85	38.11	38.37
Efficiency ¹	η	[%]	≥20.1	≥20.4	≥20.6	≥20.9	≥21.1
IMUM PERFORMANCE AT NORMAL OPERA	TING CON	DITIONS, NM	OT ²				
Power at MPP	P _{MPP}	[W]	296.4	300.1	303.9	307.6	311.4
Short Circuit Current	I _{sc}	[A]	8.97	8.99	9.02	9.04	9.07
Open Circuit Voltage	V _{oc}	[V]	42.46	42.49	42.52	42.56	42.59
Current at MPP	I _{MPP}	[A]	8.33	8.38	8.43	8.48	8.53
Voltage at MPP	V _{MPP}	[V]	35.59	35.82	36.04	36.27	36.49
	IMUM PERFORMANCE AT STANDARD TEST Power at MPP¹ Short Circuit Current¹ Open Circuit Voltage¹ Current at MPP Voltage at MPP Efficiency¹ IMUM PERFORMANCE AT NORMAL OPERA Power at MPP Short Circuit Current Open Circuit Voltage Current at MPP	IMUM PERFORMANCE AT STANDARD TEST CONDITION Power at MPP¹ P _{MPP} Short Circuit Current¹ I _{SC} Open Circuit Voltage¹ V _{OC} Current at MPP I _{MPP} Voltage at MPP V _{MPP} Efficiency¹ IMUM PERFORMANCE AT NORMAL OPERATING CONIPOWER at MPP P _{MPP} Short Circuit Current I _{SC} Open Circuit Voltage V _{OC} Current at MPP I _{MPP}	IMUM PERFORMANCE AT STANDARD TEST CONDITIONS, STC¹ (PO Power at MPP¹ P _{MPP} [W] Short Circuit Current¹ I _{SC} [A] Open Circuit Voltage¹ V _{OC} [V] Current at MPP I _{MPP} [A] Voltage at MPP V _{MPP} [V] Efficiency¹ n [%] IMUM PERFORMANCE AT NORMAL OPERATING CONDITIONS, NMO Power at MPP P _{MPP} [W] Short Circuit Current I _{SC} [A] Open Circuit Voltage V _{OC} [V] Current at MPP I _{MPP} [A]	$\begin{array}{c ccccccccccccccccccccccccccccccccccc$	MUM PERFORMANCE AT STANDARD TEST CONDITIONS, STC¹ (POWER TOLERANCE +5 W / - 0 W) Power at MPP¹ P _{MPP} [W] 395 400 Short Circuit Current¹ I _{SC} [A] 11.13 11.16 Open Circuit Voltage¹ V _{OC} [V] 45.03 45.06 Current at MPP I _{MPP} [A] 10.58 10.64 Voltage at MPP V _{MPP} [V] 37.32 37.59 Efficiency¹ η [%] \geq 20.1 \geq 20.4 MUM PERFORMANCE AT NORMAL OPERATING CONDITIONS, NMOT² Power at MPP P _{MPP} [W] 296.4 300.1 Short Circuit Current I _{SC} [A] 8.97 8.99 Open Circuit Voltage V _{OC} [V] 42.46 42.49 Current at MPP I _{MPP} [A] 8.33 8.38	Number Number	Number Number

¹Measurement tolerances P_{MPP} ± 3%; |_{SC}; V_{OC} ± 5% at STC: 1000 W/m², 25 ± 2°C, AM 1.5 according to IEC 60904-3 • ²800 W/m², NMOT, spectrum AM 1.5


Q CELLS PERFORMANCE WARRANTY



At least 98% of nominal power during first year. Thereafter max. 0.5% degradation per year. At least 93.5% of nominal power up to 10 years. At least 86% of nominal power up to 25 years.

All data within measurement tolerances. Full warranties in accordance with the warranty terms of the Q CELLS sales organisation of your respective country.

PERFORMANCE AT LOW IRRADIANCE



Typical module performance under low irradiance conditions in comparison to STC conditions (25 $^{\circ}C$, 1000 W/m²)

TEMPERATURE COEFFICIENTS								
Temperature Coefficient of I _{SC}	α	[%/K]	+0.04	Temperature Coefficient of Voc	β	[%/K]	-0.27	
Temperature Coefficient of P _{MPP}	γ	[%/K]	-0.34	Nominal Module Operating Temperature	NMOT	[°F]	109±5.4 (43±3°C)	

PROPERTIES FOR SYSTEM DESIGN

Maximum System Voltage $V_{\scriptsize SYS}$	[V]	1000 (IEC)/1000 (UL)	PV module classification	Class II	
Maximum Series Fuse Rating	[A DC]	20	Fire Rating based on ANSI/UL 61730	TYPE 2	
Max. Design Load, Push/Pull ³	[lbs/ft ²]	75 (3600 Pa)/55 (2660 Pa)		-40°F up to +185°F	
Max. Test Load, Push / Pull ³	[lbs/ft ²]	113 (5400 Pa) / 84 (4000 Pa)	on Continuous Duty	(-40°C up to +85°C)	

QUALIFICATIONS AND CERTIFICATES

PACKAGING INFORMATION

48.0 in

1220 mm

UL 61730, CE-compliant, Quality Controlled PV - TÜV Rheinland, IEC 61215:2016, IEC 61730:2016, U.S. Patent No. 9,893,215 (solar cells), QCPV Certification ongoing.

3 See Installation Manual









1940mm



1100 mm



1656 lbs

751 ka



pallets

24



24

pallets



modules

32

Note: Installation instructions must be followed. See the installation and operating manual or contact our technical service department for further information on approved installation and use of this product.

packaging

Hanwha Q CELLS America Inc.